

Information contained on this Product Information Data Sheet is to the best of our knowledge accurate and reliable. However, no guarantee is given nor intended as conditions of handling and use of this product are beyond our control.

# Q. D. SEAL

## POLYURETHANE TIMBER & CORK PRIMER

TDSE31-1-1100

**DESCRIPTION: -**

Peerless Q.D. SEAL is a clear pre-catalysed oil modified urethane resin designed to penetrate deeply into the pores of the timber, parquetry or granwood flooring.

Q.D. SEAL is a fast drying one-pot seal with excellent film hardness and flexibility, suitable for spillages and aging.

Q.D. SEAL is recommended for use on strip timber, parquetry, and granwood flooring.

Q. D. SEAL is not recommended for use on external timber.

PHYSICAL PROPERTIES	
Appearance	Slightly viscous tan coloured liquid
Odour	Mineral solvent
Specific Gravity	0.850 ± 0.005
Percentage Volatiles	74.5 – 75.5%
Solubility in Water	Insoluble
Coverage	8 – 12 m <sup>2</sup> /litre (typical)

**DIRECTIONS FOR USE: -**

Prepare floor surface by fine sanding. Ensure total removal of all wood dust by thorough vacuuming. Apply a liberal coat of Q.D. SEAL with a lambswool applicator, applying across the timber grain and finishing with the grain. Ensure the floor stays wet for at least 15 minutes, re-applying extra Q.D. SEAL where complete penetration has occurred and the floor dried out. Provide adequate ventilation during application and work away from the sealed surface. Correct application of the seal should present a surface that has the grain emphasised and a matt finish when dry. Under normal atmospheric conditions and adequate ventilation Q.D. SEAL will be touch dry in 1 - 1 1/2 hours and ready for cut back procedure in 2 hours.

NOTE: - To avoid staining the timber, stop up all nail holes after the Q.D. SEAL has dried. Before application of Beauty the floor must be cut back with steelwool and all loose fibres and dust removed. Apply Beauty in accordance with label directions.

TDGLA 001

**PEERLESS EMULSION PRODUCTS PTY. LTD. A.C.N. 004 315 619**

Head Office: 173 Grange Road, Fairfield, Victoria, Australia, 3078. TEL: (03) 9499 3161 FAX: (03) 9497 4456.

N.S.W. (02) 9674 3000 QLD. (07) 3260 1377 W.A. (08) 9362 1800 S.A. (08) 8352 4077 TAS. (03) 6234 4694 N.T. (08) 8984 3219

Ballarat (03) 5331 3688 Kalgoorlie (08) 9021 4421